

CLASSIFICATION

AWS A5.18	ER70S-6	A-Nr	1	Mat-Nr	1.5130
EN ISO 14341-A	G 42 3 M21 3Si1 / G 38 2 C1 3Si1	F-Nr	6		
		9606 FM	1		

GENERAL DESCRIPTION

Coppered solid wire for semi-automatic and automatic welding applications

Good feedability, consistent welding performance

Very good weldability, stable arc, and low spatter

High productivity

WELDING POSITIONS (ISO/ASME)



PA/1G



PB/2F



PC/2G



PD/4F



PE/4G



PF/3Gu

SHIELDING GASES (ACC. ISO 14175)

M21	Mixed gas Ar+ >15-25% CO ₂
C1	Active gas 100% CO ₂

APPROVALS

DB

+

TÜV

+

CE

+

CHEMICAL COMPOSITION (W%) TYPICAL WIRE

C

0.08

Mn

1.50

Si

0.85

MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Condition	Yield strength [N/mm ²]	Tensile strength [N/mm ²]	Elongation [%]	Impact ISO-V[D] -30°C
Typical values	AW	440	540	30	60

PACKAGING AND AVAILABLE SIZES

Diameter (mm)	0.8	1.0	1.2
15 kg spool S300	X	X	X
15 kg spool BS300	X	X	X
250 kg drum		X	X

Other sizes and packaging on request